

## PRODUCT PROFILE

GENERIC DESCRIPTION	Polyamine Epoxy
COMMON USAGE	A fiberglass-reinforced coating for protection against acids, alkalis and physical abuse. A complete system with a topcoat provides a seamless surface which can be cleaned with pressurized hot water.
COLORS	White. <b>Note:</b> Epoxies chalk and yellow with age, extended exposure to UV and artificial lighting. Lack of ventilation, incomplete mixing, miscatalyzation or the use of heaters that emit carbon dioxide and carbon monoxide during application and initial states of curing may cause amine blush, possibly affecting adhesion of subsequent topcoats.



## COATING SYSTEM

SURFACERS/FILLERS	<b>CMU &amp; Concrete:</b> Series 130, 216, 218, 219. Series 201 or 280 mixed with fumed silica (refer to Technical Bulletin 98-11R-1). Refer to the applicable product data sheet for additional information.
PRIMERS	<b>Wood &amp; Drywall:</b> Self-priming or Series 201 <b>CMU &amp; Concrete:</b> Series 201
TOPCOATS	Series 73, 84, 113, 114, 280, 282, 290, 475, 1074, 1075. Refer to the applicable topcoat data sheet for color availability and additional information.

## SURFACE PREPARATION

Prepare surfaces by method suitable for exposure and service. (See the primer/surfer/filler product data sheet and the *Fiber Reinforced Systems Installation and Application Guide* for specific recommendations.)

ALL SURFACES Must be clean, dry and free of oil, grease and other contaminants.

## TECHNICAL DATA

VOLUME SOLIDS	100% (mixed)				
RECOMMENDED DFT	25 to 40 mils (635 to 1,015 microns) per coat.				
CURING TIME	<b>Temperature</b>	<b>To Touch</b>	<b>To Topcoat</b>	<b>To Place in Service*</b>	<b>Full Cure</b>
	75°F (24°C)	4-6 hours	8-24 hours	3 days	7 days

If more than 24 hours have elapsed between coats, the Stranlok coated surface must be mechanically abraded before topcoating. **\*Note:** Severe service may require a longer curing time. Contact your Tnemec representative or Tnemec Technical Services.

VOLATILE ORGANIC COMPOUNDS .02 lbs/gallon  
(2 grams/litre)

THEORETICAL COVERAGE 1,604 mil sq ft/gal (39.4 m<sup>2</sup>/L at 25 microns). See APPLICATION for coverage rates.

NUMBER OF COMPONENTS Two: Part A and Part B

PACKAGING KITS CONSIST OF:

	PART A (Partially filled)	PART B (Partially filled)	When Mixed
Large Kit	6 gallon pail	2 gallon pail	5 gallons (18.9 L)
Medium Kit	3½ gallon pail	1 gallon pail	2½ gallons (9.46 L)
Small Kit	1 gallon can	½ gallon pail	1 gallon (3.79 L)
Touch-up/Repair Kit: Contact your Tnemec representative for more information.			

NET WEIGHT PER GALLON 10.70 ± 0.25 lbs (4.83 ± .11 kg) (mixed)

APPROX. SHIPPING WEIGHT Large Kit: 57 lbs (25.9 kg)  
Medium Kit: 29 lbs (13.2 kg)  
Small Kit: 12 lbs (5.4 kg)  
Touch-up Kit: 3 lbs (1.4 kg)

STORAGE TEMPERATURE Minimum 40°F (4°C) Maximum 90°F (32°C)  
Prior to application, the material temperature should be between 70°F and 90°F (21°C and 32°C). It is suggested the material be stored at these temperatures at least 48 hours prior to use.

Published technical data and instructions are subject to change without notice. The online catalog at [www.tnemec.com](http://www.tnemec.com) should be referenced for the most current technical data and instructions or you may contact your Tnemec representative for current technical data and instructions.  
© February 2004, by Tnemec Company, Inc.

**TECHNICAL DATA continued**

TEMPERATURE RESISTANCE	(Dry) Continuous 275°F (135°C) Intermittent 300°F (149°C)
SHELF LIFE	12 months at recommended storage temperature.
FLASH POINT - SETA	Part A and Part B: NA
HEALTH & SAFETY	This product contains chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product. <b>Keep out of the reach of children.</b>

**APPLICATION**

COVERAGE RATES Before commencing, obtain and thoroughly read the *Fiber Reinforced Systems Installation and Application Guide*.

Dry Mils (Microns)	Wet Mils (Microns)	Sq Ft/Gal (m <sup>2</sup> /Gal)
25-40 (635-1015)	25-40 (635-1015)	40-65 (3.7-6.0)

Allow for overspray and surface irregularities. Application of coating below minimum or above maximum recommended dry film thickness may adversely affect coating performance.

**Note:** If spray applied, two coats applied 30 minutes to 2 hours apart (depending on temperature) are normally required to achieve 25 to 40 mils (635-1,015 microns) DFT without runs or sags.

MIXING Use a variable speed drill with a PS Jiffy blade. Premix the entire contents of Part A. Using a flexible blade spatula empty the entire contents of the Part B container into the center of the premixed Part A and mix for a minimum of two minutes. During mixing, scrape the container wall to aid in complete blending of the two components. **Note:** The materials are packaged by weight and the ratio of Part A to Part B should not be altered. Apply the mixed material within pot life limits after agitation.

**Note:** Refer to the *Fiber Reinforced Systems Installation and Application Guide* for detailed information.

**Caution: Do not reseat mixed material. An explosion hazard may be created.**

POT LIFE 25 to 30 minutes at 70°F (21°C) 15 to 20 minutes at 80°F (27°C) 8 to 10 minutes at 90°F (32°C)  
Material temperatures above 90°F (32°C) will significantly reduce the pot life.

THINNING Normally not required.

TEMPERATURE REQUIREMENT For optimum application, handling and performance, the surface and material temperatures during application should be between 70°F and 90°F (21°C and 32°C). For application below 70°F (21°C), contact your Tnemec representative for instructions and precautions. The substrate temperature should be dry and at least 5°F (3°C) above the dew point. Temperature will affect the workability. Cool temperatures increase viscosity and decrease workability.

APPLICATION EQUIPMENT Airless spray or trowel. For detailed instructions refer to the *Fiber Reinforced Systems Installation and Application Guide*.

CLEANUP Flush and clean all equipment immediately after use with MEK or Propylene Glycol Monomethyl Ether.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating. FOR INDUSTRIAL USE ONLY.